



## Char-Carb Activated Coconut Carbon

CHAR-CARB Activated Granular Carbon is made from selected coconut shells to insure positive quality control during the manufacturing process. Virgin raw material is activated thermally in a rotary kiln steam atmosphere. By maintaining strict quality control standards, high adsorption of odors

and other contaminates from occupied air space can be achieved.

**CHAR-CARB** can also be effectively used in most liquid phase applications to remove odors, tastes, chemicals and organic compounds.

Grade CF-60			Specifications
Activity - CCI <sub>4</sub> (ASTM-D-3467)			Minimum 60%
Apparent Density (ASTM-D-2854)			Typical 0.44 - 0.49 g/cm <sup>3</sup>
Hardness (MIL-C-17605B)			Typical 97
Moisture as packed (ASTM-D-2867)			Maximum 3%
Ash (ASTM-D-2866)			Maximum 3%
Properties			Value
Surface Area (N <sub>2</sub> Bet Method)			Typical 1100-1250 m <sup>2</sup> /g
Pore Volume			Typical 0.50 cm <sup>3</sup> /g
Specific Heat at 15 °C			0.65-0.75
pH Water Extract			9.50
Туріса	l Mesh Siz	zes	
4 X 6	4 X 8	6 X 12	Oversize Maximum 5%
4 X 12	8 X 16	12 X 30	Undersize Maximum 5%

## Caution: Wet Activated Carbon Depletes Oxygen from Air.

Whenever workers enter a vessel containing carbon, all precautions must be taken since dangerously low levels of oxygen may be encountered. Atmosphere sampling and work procedures for potentially low oxygen areas should be followed.

## Standard Packaging:

200 and 50 pound fiber drums 1100 lb supersacks.

This information is believed to be accurate and reliable. Nothing herein shall be deemed to be a warranty of representation, expressed or implied, with respect to the use of such information or the use of the goods described for any particular purpose alone or in combination with other goods and/or processes, or that their use does not conflict with existing patent rights. No license is granted to practice any patented invention. It is solely for your consideration, investigation, and verification.